


DIMENSIONS



(mm)	Nominal:	Tol. min.:	Tol. max.:
A	30.8	-1.4	0.0
B	15.0	-0.2	+ 0.2
C	7.3	-0.5	0.0
D	9.7	0.0	+ 0.5
E	19.5	0.0	+ 1.0
F	7.2	-0.5	0.0
L	5.65 Nom.		
M	6.15 Nom.		
Eff. Parameters			
Ae mm²	Amin mm²	le mm	Ve mm³
60.0	49.0	67.0	4000

INDUCTANCE

MARKING

AL value (nH)	Test conditions
Nom: 3800 Min.: 2850	10 kHz, < 0.5 mT, 25 °C

No marking

LOSS FACTOR

$\tan \delta/\mu$ ($\times 10^{-6}$)	Test conditions
< 36	100 kHz, < 0.25 mT, 25 °C

NOTE

Spec. modifications	Previous	Revised
2005-06-22	L=4.65 Min. L=5.56 Max. M=6.46 Ref. Loss factor: General J material	L=5.65 Ref. M=6.15 Ref. Loss factor: Detail as indicated